

Super Flow 30

Ultra-Rapid Setting, High Performance, Flexible, Double Component Smoothing Compound

PROFESSIONAL FLOORING PRODUCTS

- Excellent Flow & Self-Smoothing Properties
- Walk On After 30 Minutes
- Install Resilient Floor Coverings After 90 Minutes
- Apply From 2mm – 15mm In One Application
- Use Over Old Adhesive Residues Including Bitumen
- Excellent Adhesion Properties Without Priming Most Substrates
- Moisture Tolerant- Use Below A DPM
- Ideal For Use Above Underfloor Heating Systems & Timber Substrates

Excellent Adhesion Without Priming Most Substrates

MOISTURE TOLERANT

Walk On After 30 Mins

LVT After 90 Mins

Tile After 45-60 Mins



TILEMASTER SUPER FLOW 30

Ultra-Rapid Setting, High Performance, Flexible, Double Component Smoothing Compound

DESCRIPTION:

Tilemaster Super Flow 30 is an ultra-rapid setting, high performance, flexible, double component smoothing and levelling floor compound, providing an underlayment where a fast track solution is required. The specially formulated powder component is mixed with a pre-gauged, protein free polymer liquid, giving a free-flowing, shrinkage compensated floor compound that can be applied from depths of 2mm – 15mm in one application.

Tilemaster Super Flow 30 has excellent flow and adhesion properties, making it suitable for a wide range of both commercial and domestic applications. These unique properties ensure that Tilemaster Super Flow 30 can be used with confidence without the need to prime the large majority of substrates. Tilemaster Super Flow 30 is moisture tolerant and can be used to smooth subfloors prior to the installation of a DPM. Tilemaster Super Flow 30 is ideal for encapsulating electric underfloor heating elements and for use over underfloor heated screeds.

Once mixed, Tilemaster Super Flow 30 will remain workable for 10 - 15 minutes and it will accept light foot traffic after 30 minutes in ideal conditions. Resilient floor coverings can be installed after 90 minutes.

PREPARATION:

Preparation of all substrates is crucial to the success and longevity of all installations. All substrates, as stated in BS 8203, must be rigid, flat, clean, dry and sound and be free of any contaminants. Anything that could compromise adhesion to the substrate, such as dust, dirt, oil, grease, laitance, sealers, waxes and curing agents will need to be mechanically removed. Ensure that all substrates and backgrounds are strong enough to carry the weight of the compound as well as all finished floor coverings and fixing materials.

When installing moisture sensitive floor coverings, the concrete or sand & cement screed should be confirmed dry by consistent moisture readings; <75% relative humidity (RH) when tested in accordance with BS 8203.

Where a structural damp proof membrane is not present or where rising damp and/or residual moisture results in moisture readings up to 98% RH, Tilemaster FAST One Coat DPM must be applied before or after the application of Tilemaster Super Flow 30. Surface laitance must be removed from concrete and sand & cement screed surfaces prior to application.

PRIMING:

Most substrates do not require priming prior to the application of Tilemaster Super Flow 30. Priming the substrate however will minimise the risk of pinholes forming, allow for the best flow properties and also prolong the working time of the product. Priming the substrate prior to application whilst not necessary, is considered "best practice".

Where priming is necessary, prime the substrate using Tilemaster Primeplus or Prime+ Grip by following the instructions below.

Porous Surfaces: Suitably prepared and sufficiently dry substrates, prime with Tilemaster Primeplus diluted 1 part Primeplus to 3 parts water. If the substrate is overly porous then further coats of diluted primer may be required.

Non-Porous Surfaces: Substrates such as Tilemaster FAST One Coat DPM, flooring grade asphalt & bitumen, steel and existing vinyl, ceramic, porcelain and natural stone tiles should be primed with one coat of Tilemaster Prime+ Grip.

Primers should be used in accordance with instructions printed on the bottle and must be allowed to dry before applying Tilemaster Super Flow 30.

MIXING & APPLICATION:

Shake the pre-gauged bottle of liquid polymer and pour into a suitable clean mixing bucket. Add the powder component slowly whilst mixing with an electric paddle and continue to mix until a smooth and lump free consistency is obtained. Once mixed do not add further polymer liquid or water.

N.B: Once mixed, Tilemaster Super Flow 30 will remain workable in the bucket for 10 - 15 minutes at 23°C. Due to the ultra-rapid setting properties of Tilemaster Super Flow 30, it is important to apply the mixed product without delay.

Pour the compound onto the prepared surface and trowel down lightly to a depth between 2mm and 15mm. The use of a spiked roller is recommended immediately in order to remove entrapped air and smooth out flow lines. The setting time will then depend on atmospheric conditions/temperatures - it will be slowed by lower temperatures and accelerated by higher temperatures.

If the substrate is impervious or if it contains old adhesive residues, Tilemaster Super Flow 30 should be applied to a minimum overall thickness of 3mm. This is to ensure the uniform drying of the adhesives that are subsequently applied to the Tilemaster Super Flow 30, whilst also ensuring that there is no interaction between the new adhesive and old adhesive residues.

SETTING AND COVERING:

In ideal conditions, Tilemaster Super Flow 30 will accept light foot traffic after 30 minutes. Tilemaster Super Flow 30 must be left to dry before applying the final floor covering. This is typically after 90 minutes for resilient flooring such as LVT and vinyl, however, this can vary depending on the choice of surface flooring. Thicker applications may require a longer time to dry prior to applying floor coverings. If there is no air flow within site conditions, the drying time may be restricted.

TILEMASTER **SUPER FLOW 30**

Ultra-Rapid Setting, High Performance, Flexible, Double Component Smoothing Compound

Screed classification	CT-C16-F6 to EN13813:2002
Working time @ 23°C	10 - 15 minutes
Time to foot traffic @ 23°C	30 minutes
Application thickness	2mm – 15mm
Compressive strength N/mm ² (BS EN 13892-2)	1 day > 9.0 7 day > 10.5 28 day > 16.0
Flexural strength N/mm ² (BS EN 13892-2)	1 day > 3.0 7 day > 3.5 28 day > 6.0
Coverage	A 20kg bag and 4.5Ltr liquid unit will cover 4.5m ² at 3mm thickness
Flow properties using 30mm x 50mm flow ring	135mm – 150mm
Minimum application temperature	5°C
Shelf life	Stored correctly the powder component has a shelf life of 12 months and 12 months for the latex liquid
Colour	Powder – Beige Liquid – White
Pack size	Bag – 20kg Liquid – 4.5 Ltrs
Note	All work must be carried out in accordance with British Standard Code of Practice.

HEALTH AND SAFETY

Tilemaster Super Flow 30 contains cement. Contact with moisture or gauging water sets off an alkaline reaction which may cause skin irritation and/or caustic burns to mucous membranes (e.g. eyes). Irritant to respiratory system. Risk of serious damage to eyes, therefore avoid contact with eyes and prolonged contact with skin. Do not breathe dust. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin, take off immediately all contaminated clothing, and wash immediately with plenty of water and soap. Wear suitable gloves (e.g. cotton gloves soaked in nitrile) and eye/face protection. If swallowed, seek medical advice immediately and show this container or label. Keep out of reach of children. Low in chromates.

For further information refer to the Material Safety Data Sheet.

The information contained on this Technical Data Sheet is given voluntarily and in good faith. It is to the best of our knowledge true and accurate; however, it may contain information which is inappropriate under certain conditions of use. The company cannot accept responsibility for any loss or damage due to inappropriate use or the possibility of variations of working conditions and of workmanship outside our control.

NOTE: This product is not designed nor potentially suitable for the repair or making good of newly installed screeds that have been installed being knowingly faulty, out of manufacturers specification or with defects outside of the manufacturers or installers usual standards and specification.