DESSO Textile floor covering - Tiles & Planks

Essence Structure

Specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1/10 “					
Aspect	ISO 2424		Structured loop pile					
Dye method			Solution dyed					
Dimension	EN ISO 24342	cm x cm	50 x 50 & 100 x 25 / 19,68” x 19,68” & 39,36” x 9,84” (20 tiles / 20 planks per box)					
Primary backing	ISO 2424		Polyester fleece					
Secondary backing	ISO 2424		ProBase - modified bitumen.					
Pile fibre composition	ISO 2424		BCF Polyamide 6					
Total thickness	ISO 1765	mm	6.5	inch	0.3			
Effective pile thickness	ISO 1766	mm	2.8	inch	0.11			
Total mass	ISO 8543	g/m²	4050	oz/yd²	119.5			
Total pile mass	ISO 2424	g/m²	580	oz/yd²	17.1			
Effective pile mass	ISO 8543	g/m²	320	oz/yd²	9.4			
Pile density	ISO 8543	g/cm³	0.114	lb/in³	0.0041			
Number of tufts	ISO 1763	/dm²	1580	/yd²	132104			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307		33 Commercial - heavy use					
Luxury rating	EN 1307		LC 1					
Dimensional stability	EN 986	%	≤ 0,2					
Impact sound reduction ΔL_W	ISO 10140	dB	24					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α_s	0.00	0.02	0.06	0.17	0.29	0.37
Noise reduction	ISO 354	α_w	0.15					
Thermal resistance	ISO 8302	m².K/W	0.071					
Flammability	EN 13501-1		Bfl - s1 (loose laid tested)					
Prodis - GUT	www.pro-dis.info		0FCE0C9C					

CE
EN 14041
0493-CPR-0002

Manufactured by:
Tarkett BV
Taxandriaweg 15
NL - 5142 PA Waalwijk

Bfl-s1 DS

Quality- and Environmental Management System Certification ISO 9001 & ISO 14001

DESSO flooring products are to be installed in full accordance with Tarkett’s installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. DESSO flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20221202

Tarkett BV
Taxandriaweg 15
NL-5142 PA Waalwijk

Tarkett